

# C3-473

## One Pack Polyurethane Coating



### Description

C3-473 is a polyurethane based coating.

It has been developed for use in protective coating applications for items such as upholstery, tents and tarpaulins.

### Application method(s)

C3-473 can be applied by conventional coating techniques i.e. knife-over-roller, air knife etc.

### Curing

Solvent should be removed from the freshly coated fabric at 80°C-110°C.

Allow 3 days for the coated fabric to fully dry.

### Usage Notes

Clean equipment with Toluene.

Thinning is not necessary.

### Health & Safety

See SDS. If you need a copy of the latest version please contact [sales@itac.uk.com](mailto:sales@itac.uk.com).

### Packing and Storage

5 litre open top pails, 25 litre open top pails and 200 litre open top drums.

Store in a cool dry place between 5°C and 30°C .

Typical properties for this product are given based on ITAC manufacturing experience. They are not a specification of the product.

ITAC Limited,  
Bankfield Mills, Bankfield Street,  
Stoneclough, Radcliffe,  
Manchester M26 1AS

Tel: + 44 (0)1204 573736  
email: [sales@itac.uk.com](mailto:sales@itac.uk.com)  
web: [www.itacadhesives.com](http://www.itacadhesives.com)

Reg in Eng No 499145  
VAT reg No 145 4337 73



# C3-473

## One Pack Polyurethane Coating

Typical Properties	Value	Units	Test method
Base Polymer	Polyurethane	NA	
Colour	Silver Grey	NA	
Specific Gravity	1.10	NA	
Solvent(s)	Toluene, Isopropanol Alcohol	NA	
Solids Content	34-36	% by weight	
Viscosity	8,000 - 12,000	cPs	Brookfield spindle 4, speed 20 at 20°C
Flashpoint	6	°C	Closed Cup, ISO 3679
Shelf life	12 months from date of manufacture, which is printed on the label.		

Other Properties	Value	Units	Test Method

Typical properties for this product are given based on ITAC manufacturing experience. They are not a specification of the product.